

**Carpinteros No 37, Parque
Industrial Xhala, Cuautitlán
Izcalli, Edo México C.P. 54714**

Producto: DINP	FECHA DATE		
Lote: 171024	DIA MES	MES MONTH	AÑO YEAR
Cliente: A QUIEN CORRESPONDA	30	07	28

DETERMINACION	ESPECIFICACION	RESULTADO	METO DO
INDICE DE-ACIDEZ mg KOH/g ACID NUMBER	0.07 Max.	0.016	ASTM D-4662-98 ASTM D-1048-90
ACIDEZ C/AC. FTÁLICO ACIDITY AS PHTHALIC ACID %	-	-	
ACIDEZ C/AC. ACETICO ACITITY AS ACETIC ACID %	-	-	
DENSIDAD 20° C (x) 25° C () () SPECIFIC GRAVITY	0.968 - 0.979	0.973	ASTM D-1298-99
VISCOSIDAD cps 25° C () 60° C () 75° () VISCOSITY	-	-	ASTM D-4878-98
TEMPERATURA DE INFLAMACIÓN °C (C.O.C.)	220 Min.	234	ANSI/ASTM D-92-01
COLOR APHA (x) GARDNER ()	25 Max	5	ASTM D-1045-90
% HUMEDAD (KARL FISHER) % WATER	0.1 Max	0.027	ASTM D-1533-88
INDICE DE REFRACCIÓN	1.4850 – 1.475	1.4854	
PUREZA, % PESO	99.0 Mín	99.9	ASTM D-1045-95

Observaciones:



Ing. Álvaro Morales González
Responsable de control de calidad